

FullCure®930 TangoPlus Black

Property	ASTM	Results (Metric)		Results (Imperial)	
Tensile Strength at Break	D-412	MPa	1.455	psi	211
Tensile Modulus at 20% Strain	D-413	MPa	0.146	psi	21
Tensile Modulus at 30% Strain	D-414	MPa	0.185	psi	27
Tensile Modulus at 50% Strain	D-415	MPa	0.263	psi	38
Elongation at Break	D-412	%	218	%	218.0
Compressive Set, 22 Hr, 750C	D-395	%	4.4	%	4
Shore A Hardness	D-2240	Scale D	27	Scale D	27
Ross Flex	D-1052		Above 150,000		Above 150,000
Tensile Tear Resistance	D-624	Kg/cm	3.47	Lb/in	20
Tg	DSC (-80°C+100°C)	°C	-9.6	°F	15