

Objet VeroWhitePlus (RGD835) - rigid, white material

Property	ASTM	Metric		Imperial	
Tensile Strength	D-638-03	55-60	MPa	7,250-9,450	psi
Modulus of Elasticity	D-638-04	2,000-3,000	MPa	290,000-435,000	psi
Elongation at Break	D-638-05	10-25	%	10-25	%
Flexural Strength	D-790-03	75-110	MPa	11,000-16,000	psi
Flexural Modulus	D-790-04	2,200-3,200	MPa	320,000-465,000	psi
Izod Notched Impact	D-256-06	20-30	J/m	0.375-0.562	ft lb/in
HDT at 0.45 MPa	D-648-06	45-50	°C	113-122	°F
Water Absorption	D570-98 24 Hr	1.1-1.5	%	1.1-1.5	%

